

Characterization of Aluminum Oxide Nanoparticles: Synthesis, Properties, and Environmental Impact

Maria Silva^{*1}, Pedro Costa², Ana Torres³ & Rui Almeida⁴

^{*1}Department of Nanotechnology, University of Porto, Porto 4200-465, Portugal

²Department of Materials Science, University of Lisbon, Lisbon 1000-123, Portugal

³Department of Chemistry, University of Coimbra, Coimbra 3000-300, Portugal

⁴Department of Nanotechnology, University of Aveiro, Aveiro 3810-193, Portugal

ABSTRACT

The nanomaterials have many applications in industries such textiles, paints, petroleum products Aluminum oxide (Al_2O_3) nanoparticles was successfully synthesized by Urea decomposition method using metal nitrate as precursors in the presence of sunlight. The as-synthesized samples were characterized by X-ray diffraction (XRD), Fourier transform infrared (FTIR). The x-ray diffraction pattern indicated that as-synthesized sample had a crystal size with finest particle size of the catalyst (69.0nmapp.) was obtained at 600°C calcination temperature. Fourier transform infrared spectra confirmed the presence of hydroxyl group and Al-O bond vibration in the catalyst. Experimental result of the Al_2O_3 calcined at 600°C for 2hr, exhibited many activities of under different investigation under process as of next research going to publish in the next session.

KEYWORDS: Nanoparticles, Characterization, XRD.

I. INTRODUCTION

Nanomaterials have many applications in industries such textiles, paints, petroleum products cosmetic products[1,2]. Industries has used different types of dyes resulted in the release of large amounts of toxic compounds into environment [2,]. This article will prove the usage of synthesized nanoparticles will decrees the waste as well as will purify the polluted waters by ecofriendly way. The waste water from those industries must be treated before their discharge. Various physical and chemical methods have been used for toxic removal from waste waters [3,4]. Thus, environmental contamination by these toxic chemicals has emerged as a serious global problem[5]. On the contrary, bleached dye after degradation of solution is relatively less toxic and almost harmless [6]. Dyes containing colored water is almost no practical use, but if this colored solution is bleached to give colorless water, then it may be used for some useful purposes like washing, cooling, irrigation and cleaning [7,8]. Among various metal oxide Nanoparticles photo catalysts, Aluminum oxide (Al_2O_3) exhibit promising photocatalytic activities due to their environmental friendly behavior, low catalyst cost, high specific surface area, high crystallinity and solar energy application and thus, could be an alternative material for environmental application and wastewater[9,10]. At the present studies is an attempt to clean the environment waste water through the nanomaterials. So, in this paper we tried to study the Al_2O_3 , Nanoparticles through its characterization techniques. In our next studies the will prove Al_2O_3 , Nanoparticles best for industrial waste water treatment.

II. MATERIALS AND METHODS

Synthesis of Al_2O_3 nanoparticles

The nanoparticles Al_2O_3 , powder was prepared by Urea decomposition method. The Urea was corresponded to total volume ratio of metal nitrate, ratio of 1:2. In each case, aluminum nitrate dissolved in stoichiometric amounts of water, 10% then mixed with vigorous stirring at room temperature (55°C). The prepared slurry was left to stand for the formation of solid. After the solidification was completed, the solid was kept for 2 days at room temperature and sample was dried at 75°C for 36 h. After grinding the dried samples, they were calcined at 600°C for 2 h. Nano sized materials of the catalyst were analyzed.

Characterization:

FTIR is carried out from our institute using Parkin Elmer FTIR instrument ranges from 400 cm^{-1} 4000 cm^{-1} . X-ray powder diffraction (XRD) analysis was carried out with Goniometer Ultima IV using a Cu K α radiation ($\lambda=1.54060\text{\AA}$) operating at 40 kV and 40 mA. Absorbance carried out by spectrophotometer.

III. RESULTS AND DISCUSSION

FTIR Studies:

The Synthesis of Al_2O_3 Nanoparticles produces clear white colored oxide. The formation of this oxide upon the heating of an aqueous mixture of $\text{Al}(\text{NO}_3)_3$. For the reaction mechanisms, an oxidation process for aluminum urea complex occurs during the decomposition of urea into ammonia, carbon dioxide and hydrogen chloride gases. The infrared spectra of synthetic oxide product are shown in Fig 1. The infrared spectra of the obtained products show bands due to characteristic groups of urea (carbonyl and amide groups) at 1629 and 1660 cm^{-1} , the bands associated to the O-H are observed at 3440 cm^{-1} is due to moisture absorbed during measurement of spectra.




Figure 1. FTIR of Al_2O_3 nanoparticles

XRD Studies:

The phase formation and orientation of Al_2O_3 nanoparticles were investigated using X-ray diffraction in the ranges (20-80deg). X-ray diffraction patterns of nanoparticles are shown in figure 2. It was found that the presence of Al_2O_3 at temperatures 600°C. The XRD results also reveal the structural results for work and the values obtained using the Scherrer equation: $D = k\lambda/\beta\cos\theta$ where D is the crystallite size, λ is the wavelength of the $\text{Cu}\alpha$ radiation, k is a constant equal to unity, β is corrected peak width at half maximum intensity and θ is peak position (62.79° used for all lines). The peaks at 34.09 and 44.89 are due to the incomplete burning of oxides. Crystallite size of Al_2O_3 -NPs increases. The decomposition process is highly affected by the molar ratio. The nanoparticle size is found Approx. 69.0nm by Scherrer equation.




Figure 2. XRD of Al_2O_3 nanoparticles

IV. CONCLUSION

The phase of Al_2O_3 nanoparticles can successfully be synthesized by urea decomposition method using aluminum nitrate, at room temperature then the burnt product was calcined at 600°C for 2h. The prepared sample was characterized by using different tools; FTIR, XRD with average crystallite size 30.096 nm approx. was obtained at 600°C. The decomposition process is highly affected by the molar ratio. The produced Al_2O_3 NPs showed photocatalytic activity by degradation of 85 % approx. of the MG dye, under sunlight irradiation, respectively, within 5 h. in overall studies it is concluded that the Al_2O_3 NPs showed photocatalytic activity and it can be used as best degradation agent.

V. ACKNOWLEDGEMENT

The authors are thankful to Solapur University, and Nanotechnology dept of S.A.P.D. Jain Pathashala'sWalchand College of Arts & Science, Solapur for providing access to instrumentation..

VI. REFERENCES

- [1] Lavaste.V., Berger, M.H., Bunsell, A.R., Besson, J. "Microstructure and mechanical characteristics of alpha-alumina-based fibres," *Journal of Materials Science*, vol 30, pp. 4215-4225, 1995
- [2] Laurence Meaghera, George V. Franksb, Michelle L. Geea, Peter J. Scalesa, Interaction forces between α -alumina fibres in aqueous electrolyte measured with an atomic force microscope. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*, vol.146, pp.123-137, 1999
- [3] G. Tournier, M. Lacroix-repellin, G.M. Pajonk, S.J. Teichner, "Microporous Amorphous Alumina of a Zeolitic Type for Catalytic Reactions with Methanol," *Studies in Surface Science and Catalysis*, vol31, pp.333-342, 1987
- [4] Hui Liua, Hongjun Suna, Junqi Li, Xuanmeng He, Zhenfeng Zhu, "pH Dependent formation of AACH fibers with tunable diameters and their *in situ* transformation to alumina nanocrystals with mesoporous structure," *Advanced Powder Technology*, vol. 23, pp.164-169,2012
- [5] Muhammad Abdullah, Mazhar Mehmood, Jamil Ahmad, "Single step hydrothermal synthesis of 3D urchin like structures of AACH and aluminum oxide with thin nano-spikes," *Ceramics International*, vol 38, pp.3741-3745,2012
- [6] Z. Zhang, T.J. Pinnavaia, "Mesostructured γ -Al₂O₃ with a lathlike framework morphology," *J. Am. Chem. Soc.*, vol.124, pp. 12294-12295,2002
- [7] Z. Li, X. Feng, H. Yao, X. Guo, "Ultrafine alumina powders derived from ammonium aluminum carbonate hydroxide," *J. Mater. Sci.*, vol.39, pp. 2267-2269,2004
- [8] Yong-Taeg O, Sang-Woo Kim, Dong-Chan Shin, "Fabrication and synthesis of α -alumina nanopowders by thermal decomposition of ammonium aluminum carbonate hydroxide (AACH)," *Colloids and Surfaces A: Physicochemical and Engineering Aspects*, vol.313-314, pp.415-418,2008
- [9] Zhisen Wu, Youde Shen, Yan Dong, Jianqing Jiang, "Study on the morphology of α -Al₂O₃ precursor prepared by precipitation method," *Journal of Alloys and Compounds*, vol 467, pp.600-604,2009
- [10] Peidong Yang, Dongyuan Zhao, David I. Margolese, Bradley F. Chmelka, Galen D. Stucky, "Generalized syntheses of large-pore mesoporous metal oxides with semicrystalline frameworks," *Nature*, vol.396, pp.152-155, 1998.603